



Anti-Static Coating

FMRD Technical Data Sheet

Standard Product Construction:

Anti Static Coating



Technical Data:

Unit of Measure 3M Test Method BEF Anti Stat- Series 996					
Thickness	mils (micron)		6.9 (175.3)	10 (254)	
Haze		%	211	0 - 1.3	0 - 1.6
Break	DW	lb/in	209	min 146	min 146
Strength	CW	lb/in	209	min 170	min 170
Break	DW	%	209	min 97	min 97
Elongation	CW	%	209	min 49	min 49
Heat Shrink	DW	%	85C/15min	0 - 0.2	0.15 - 0.29
	CW	%	85C/15min	0 - 0.2	-0.4 - 0.10
Color		L*	1038	min 95.6	min 95.6
Color		A*	1038	-0.7 - -0.15	-0.7 - -0.15
Color		B*	1038	-0.1 - 0.7	0 - 1.4

Sample rolls are available for BEF Anti-stat Series- 996 at 6.9 mil. Sheet samples and hand rolls are available in more thicknesses.